

### WHY CHOOSE ACTÍVA® BLACKJACK CLAY?

Blackjack is a high plasticity blend of screened clays that provide a smooth texture perfect for everyday use.

### IS ACTÍVA® BLACKJACK EARTHENWARE OVEN-SAFE?

Because of its porosity after firing, Blackjack White Earthenware is not intended to be used in the microwave.

### IS ACTÍVA® BLACKJACK MADE IN THE USA?

ACTÍVA proudly uses a blended mixture of clays mined in East Texas, USA.

### GLAZE RECOMMENDATIONS

Blackjack clay provides an excellent base for glazes & coloring oxides and works well with most standard glazes.

For firing, leave the bottom of the piece unglazed and place on the kiln shelf.

*Always test fire for glaze compatibility.*

*Earthenware pieces are not waterproof after firing.*

## ACTÍVA® Blackjack White Earthenware Clay



ACTÍVA Blackjack White Earthenware Clay is a versatile and user-friendly earthenware clay made from a blend of natural clays and minerals. When wet, it has a light gray color but transforms into a smooth white talc body when fired.

This clay is suitable for various pottery techniques, including hand modeling, hand building, slab rolling, and wheel throwing. It offers excellent plasticity and is ideal for artists of all levels, from beginners to professionals.

Featuring a firing range between cone 06 and cone 04, this clay is well-suited for use in classrooms and with a personal home kiln.

Firing range: Cone 06-04 (2269°F - 2320°F)  
Moisture content: 16-20%  
Firing shrinkage at Cone 6: 10%  
Porosity (water absorption at Cone 6): 14%  
Texture: Smooth  
Wet color: Gray  
Firing color: White  
Non-toxic



samuel@activaproducts.com  
P: 903-938-2224  
F: 903-938-3899  
www.activaproducts.com